

6×7+FC/IWS

公称直径 Nominal diameter		近似重量 Apprximate weight		公称抗拉强度 Nominal Tensile Strength, MPa					
				1670		1770		1870	
				最小破断拉力 Min. breaking strength,kN					
d	允许偏差 Tolerance	纤维芯 FC	钢芯 IWS	纤维芯 FC	钢芯 IWS	纤维芯 FC	钢芯 IWS	纤维芯 FC	钢芯 IWS
mm	%	kg/100m		kN					
6	+6 0	12.6	13.9	20.0	21.6	21.2	22.9	22.4	24.2
8		22.5	24.8	35.5	38.4	37.6	40.7	39.7	43.0
10		35.1	38.7	55.4	60.0	58.8	63.5	62.1	67.1
12		50.5	55.7	79.8	86.3	84.6	91.5	89.4	96.7
14		68.8	75.9	108.7	117.5	115.2	124.5	121.7	131.6
16		89.9	99.1	141.9	153.5	150.4	162.7	158.9	171.9
18		113.7	125.4	179.6	194.2	190.4	205.9	201.2	217.5
20		140.4	154.8	221.8	239.8	235.1	254.2	248.3	268.5
22		169.9	187.3	268.3	290.2	284.4	307.5	300.5	324.9
24		202.2	222.9	319.4	345.3	338.5	366.0	357.6	386.7

6×19+FC/IWS/IWR

公称直径 Nominal diameter		近似重量 Approximate weight		公称抗拉强度 Nominal Tensile Strength, MPa					
				1670		1770		1870	
				最小破断拉力 Min. breaking strength,kN					
d	允许偏差 Tolerance	纤维芯 FC	钢芯 IWS/ IWR	纤维芯 FC	钢芯 IWS/IWR	纤维芯 FC	钢芯 IWS/IWR	纤维芯 FC	钢芯 IWS/IWR
mm	%	kg/100m		kN					
6	+6 0	12.5	13.7	18.5	20.0	19.6	21.2	20.7	22.4
8		22.1	24.4	32.8	35.5	34.8	37.6	36.7	39.7
10		34.6	38.1	51.3	55.4	54.3	58.8	57.4	62.1
12		49.8	54.9	73.8	79.8	78.2	84.6	82.7	89.4
14		67.8	74.7	100.5	108.7	106.5	115.2	112.5	121.7
16		88.6	97.5	131.2	141.9	139.1	150.4	147.0	158.9
18		112.1	123.4	166.1	179.6	176.1	190.4	186.0	201.2
20		138.4	152.4	205.1	221.8	217.4	235.1	229.6	248.3
22		167.5	184.4	248.1	268.3	263.0	284.4	277.9	300.5
24		199.3	219.5	295.3	319.4	313.0	338.5	330.7	357.6
26		233.9	257.6	346.6	374.8	367.36	397.2	388.1	419.7
28		271.3	298.7	401.9	434.7	426.0	460.7	450.1	486.7
30		311.4	342.9	461.4	499.0	489.1	528.9	516.7	558.8
32		354.3	390.1	525.0	567.7	556.4	601.7	587.9	635.7
34		400.0	440.4	592.7	640.9	628.2	679.3	663.6	717.7
36		448.4	493.8	664.4	718.6	704.2	761.6	744.0	804.6

注：根据顾客需要，还可提供其他规格、抗拉强度的产品 NOTE:Providing engineer design sa per customer's request

一般用途钢丝绳 技术参数 Technical parameter

6×37+FC/IWS/IWR

公称直径 Nominal diameter		近似重量 Approximate weight		公称抗拉强度 Nominal Tensile Strength, MPa					
				1670		1770		1870	
				最小破断拉力 Min. breaking strength,kN					
d	允许偏差 Tolerance	纤维芯 FC	钢芯 IWS/ IWR	纤维芯 FC	钢芯 IWS/IWR	纤维芯 FC	钢芯 IWS/IWR	纤维芯 FC	钢芯 IWS/IWR
mm	%	kg/100m		kN					
8	+6 0	22.1	24.4	31.5	34.1	33.4	36.1	35.3	38.2
10		34.6	38.1	49.3	53.3	52.2	56.5	55.2	59.7
12		49.8	54.9	70.9	76.7	75.2	81.3	79.4	85.9
14		67.8	74.7	96.6	104.4	102.3	110.7	108.1	116.9
16		88.6	97.5	126.1	136.4	133.7	144.5	141.2	152.7
18		112.1	123.4	159.6	172.6	169.2	182.9	178.7	193.3
20		138.4	152.4	197.1	213.1	208.9	225.9	220.7	238.6
22		167.5	184.4	238.4	257.8	252.7	273.3	267.0	288.7
24		199.3	219.5	283.8	306.9	300.8	325.2	317.8	343.6
26		233.9	257.6	333.0	360.1	353.0	381.7	372.9	403.3
28		271.3	298.7	386.2	417.7	409.4	442.7	432.5	467.7
30		311.4	342.9	443.4	479.5	469.9	508.2	496.5	536.9
32		354.3	390.1	504.5	545.5	534.7	578.2	564.9	610.8
34		400.0	440.4	569.5	615.8	603.6	652.7	637.7	689.6
36		448.4	493.8	638.5	690.4	676.7	731.8	714.9	773.1
38		499.6	550.2	711.4	769.3	754.0	815.3	796.6	861.4
40		553.6	609.6	788.2	852.4	835.4	903.4	882.6	954.4

注：根据顾客需要，还可提供其他规格、抗拉强度的产品 NOTE:Providing engineer design sa per customer's request

一般用途钢丝绳 技术参数 Technical parameter

6×24+7FC

公称直径 Nominal diameter		近似重量 Approximate weight	公称抗拉强度 Nominal Tensile Strength, MPa		
d	允许偏差 Tolerance		1670	1770	1870
			最小破断拉力 Min. breaking strength		
mm	%	kg/100m	kN		
6	+7 0	11.4	16.8	17.8	18.8
8		20.4	29.9	31.7	33.5
10		31.8	46.8	49.6	52.4
12		45.8	67.3	71.4	75.4
14		62.3	91.6	97.1	102.6
16		81.4	119.7	126.9	134.0
18		103.0	151.5	160.6	169.6
20		127.2	187.0	198.2	209.4
22		153.9	226.3	239.9	253.4
24		183.2	269.3	285.5	301.6
26		215.0	316.1	335.0	354.0
28		249.3	366.6	388.6	410.5
30		286.2	420.8	446.0	471.2
32		325.6	478.8	507.5	536.2
34		367.6	540.5	572.9	605.3
36		412.1	606.0	642.3	678.6
38		459.2	675.2	715.6	756.1
40		508.8	748.2	793.0	837.8

注：根据顾客需要，还可提供其他规格、抗拉强度的产品 NOTE:Providing engineer design sa per customer's request