

公称直径 Diameter mm	GB/T 4357-2009抗拉强度Tensile Strength MPa					执行标准 Standard
	SL	SM	SH	DM	DH	
0.30		2370-2650	2660-2940	2370-2650	2660-2940	GB/T 4357, JIS G3521, JIS G3522, DIN17223, BS5216, EN10270-1, AS1472, ASTM A227, ASTM A228, ISO 8458-2, or customer's request
0.32		2350-2630	2640-2920	2350-2630	2640-2920	
0.34		2330-2600	2610-2890	2330-2600	2610-2890	
0.36		2310-2580	2590-2890	2310-2580	2590-2890	
0.38		2290-2560	2570-2850	2290-2560	2570-2850	
0.40		2270-2550	2560-2830	2270-2550	2570-2830	
0.43		2250-2520	2530-2800	2250-2520	2570-2800	
0.45		2240-2500	2510-2780	2240-2500	2570-2780	
0.48		2220-2480	2490-2760	2240-2500	2570-2760	
0.50		2200-2470	2480-2740	2200-2470	2480-2740	
0.53		2180-2450	2460-2720	2180-2450	2460-2720	
0.56		2170-2430	2440-2700	2170-2430	2440-2700	
0.60		2140-2400	2410-2670	2140-2400	2410-2670	
0.63		2130-2380	2390-2650	2130-2380	2390-2650	
0.65		2120-2370	2380-2640	2120-2370	2380-2640	
0.70		2090-2350	2360-2610	2090-2350	2360-2610	
0.80		2050-2300	2310-2560	2050-2300	2310-2560	
0.85		2030-2280	2290-2530	2030-2280	2290-2530	
0.90		2010-2260	2270-2510	2010-2260	2270-2510	
0.95		2000-2240	2250-2490	2000-2240	2250-2490	
1.00	1720-1970	1980-2220	2230-2470	1980-2220	2230-2470	
1.05	1710-1950	1960-2220	2210-2450	1960-2220	2210-2450	
1.10	1690-1940	1950-2190	2200-2430	1950-2190	2200-2430	
1.20	1670-1910	1920-2160	2170-2400	1920-2160	2170-2400	
1.25	1660-1900	1910-2130	2140-2380	1910-2130	2140-2380	
1.30	1640-1890	1900-2130	2140-2370	1900-2130	2140-2370	
1.40	1620-1850	1870-2100	2110-2340	1870-2100	2110-2340	
1.50	1600-1840	1850-2080	2090-2310	1850-2080	2090-2310	
1.60	1590-1820	1830-2050	2060-2290	1830-2050	2060-2290	
1.70	1570-1800	1810-2030	2040-2260	1810-2030	2040-2260	
1.80	1550-1780	1790-2010	2020-2240	1790-2010	2020-2240	
1.90	1540-1760	1770-1990	2000-2220	1770-1990	2000-2220	
2.00	1520-1750	1760-1970	1980-2200	1760-1970	1980-2220	
2.10	1510-1730	1740-1960	1970-2180	1740-1960	1970-2180	
2.25	1490-1710	1720-1930	1940-2150	1720-1930	1940-2150	
2.40	1470-1690	1700-1910	1920-2130	1700-1910	1920-2130	
2.50	1460-1680	1690-1890	1900-2110	1690-1890	1900-2110	
2.60	1450-1660	1670-1880	1890-2100	1670-1880	1890-2100	
2.80	1420-1640	1650-1850	1860-2070	1650-1850	1860-2070	
3.00	1410-1620	1630-1830	1840-2040	1630-1830	1840-2040	
3.20	1390-1600	1610-1810	1820-2020	1610-1810	1820-2020	
3.40	1370-1580	1590-1780	1790-1990	1590-1780	1790-1990	
3.60	1350-1560	1570-1760	1770-1970	1570-1760	1770-1970	
3.80	1340-1540	1550-1740	1750-1950	1550-1740	1750-1950	
4.00	1320-1520	1530-1730	1740-1930	1530-1730	1740-1930	
4.25	1310-1500	1510-1700	1710-1900	1510-1700	1710-1900	
4.50	1290-1490	1500-1680	1690-1880	1500-1680	1690-1880	
4.75	1270-1470	1480-1670	1680-1840	1480-1670	1680-1840	
5.00	1260-1450	1460-1650	1660-1830	1460-1650	1660-1830	
5.30	1240-1430	1440-1630	1640-1820	1440-1630	1640-1820	
5.60	1230-1420	1430-1610	1620-1800	1430-1610	(1620-1800)	
6.00	1210-1390	1400-1580	1590-1770	1400-1580	(1590-1770)	