

结构	公称直径 Nominal Diameter mm	允许偏差 Tolerance mm	绳最小破断拉力 Min B/L N		断裂伸长率 %	残余回转数 转	每米重量 g/m
			标准	最小			
3×3	0.32	±0.02	125	116	≤3.0	≤3	0.33~0.37
	0.41	±0.02	195	180	≤3.0	≤3	0.52~0.58
	0.51	±0.03	268	248	≤3.0	≤3	0.76~0.84
	0.63	±0.03	420	390	≤3.0	≤3	1.21~1.37
7×3	0.60	±0.03	440	410	≤3.5	≤3	1.27~1.38
	0.91	±0.05	950	880	≤3.5	≤3	2.90~3.14
	1.29	±0.06	1400	1350	≤3.5	≤3	5.50~5.80
7×4	0.86	±0.04	865	800	≤3.5	≤3	2.43~2.69
1×19	0.63	+0.00	620	590	≤3.0	≤3	1.71~1.89
	0.60	-0.06 ±0.03	620	590	≤3.0	≤3	1.64~1.78
1×18	0.63	±0.03	610	550	≤3.0	≤3	1.64~1.89
3+9	0.63	±0.03	580	530	≤3.0	≤3	1.71~1.89
8×7+1×19	2.12	±0.08	4900	4700	≤3.5	≤3	16.7~17.70
	1.74	±0.08	3835	3685	≤3.5	≤3	11.52~12.1
1×3+5×7	1.21	±0.06	1470	1400	≤3.0	≤3	5.1~5.64
	0.92	±0.05	1060	980	≤3.0	≤3	3.29~3.63
6×7+IWS	1.62	±0.04	3200	2960	≤3.0	≤3	9.71~10.73
	2.00	+0.1 0	4300	4200	≤3.0	≤3	16.20~16.95