

1×7

公称直径 Nominal Diameter	绳金属总断面积 Cross Section	伸长率 Elongation		绳最小破断拉力 Min B/L	参考重量 Approximate Weight
		弹性 Elastic	永久 Permanent		
mm	mm ²	不大于， % Not Exceed		kN	kg/100m
0.9	0.51	0.8	0.2	0.90	0.41
1.0	0.62			1.03	0.50
1.2	0.91			1.52	0.74
1.4	1.25			2.08	1.01
1.5	1.42			2.25	1.15
1.6	1.74			2.77	1.42
1.8	2.01			3.19	1.63
2.0	2.52			4.02	2.05

1×19

公称直径 Nominal Diameter	绳金属总断面积 Cross Section	伸长率 Elongation		绳最小破断拉力 Min B/L	参考重量 Approximate Weight
		弹性 Elastic	永久 Permanent		
mm	mm ²	不大于， % Not Exceed		kN	kg/100m
1.0	0.60	0.8	0.2	1.06	0.49
1.2	0.87			1.52	0.70
1.4	1.18			2.08	0.96
1.5	1.36			2.39	1.10
1.6	1.54			2.59	1.25
1.8	1.98			3.29	1.59
2.0	2.42			4.06	1.96
2.5	3.77			6.01	3.07
2.8	4.73			7.53	3.84
3.0	5.42			8.63	4.41
3.5	7.37			11.74	5.99
3.8	8.62	0.9		13.72	7.23
4.0	9.55			15.34	7.84
4.5	12.10			19.41	9.92
4.8	13.75			22.10	11.29

6×7-WSC

公称直径 Nominal Diameter	绳金属总断面积 Cross Section	伸长率 Elongation		绳最小破断拉力 Min B/L	参考重量 Approximate Weight
		弹性 Elastic	永久 Permanent		
mm	mm ²	不大于， % Not Exceed		kN	kg/100m
1.0	0.58	0.9	0.2	1.00	0.50
1.1	0.68			1.17	0.58
1.2	0.79			1.35	0.67
1.4	1.02			1.76	0.87
1.5	1.15			1.99	0.98
1.6	1.33			2.29	1.13
1.8	1.63			2.81	1.39
2.0	1 96			3.38	1.67
2.5	3.21			5.45	2.73
2.8	3.92			6.45	3.34
3.0	4.43			7.28	3.77
3.5	6.31	10.37		5.37	
4.0	7.87	12.92		6.70	
4.5	10.20	15.89		8.69	
4.8	11.42	17.79		9.73	
5.0	12.71	19.79		10.83	
5.5	14.89	23.19		12.68	
6.0	18.04	28.11		15.37	

6×19-WSC

公称直径 Nominal Diameter	绳金属总断面积 Cross Section	伸长率 Elongation		绳最小破断拉力 Min B/L	参考重量 Approximate Weight
		弹性 Elastic	永久 Permanent		
mm	mm ²	不大于， % Not Exceed		kN	kg/100m
1.8	1.56	0.9	0.2	2.59	1.32
2.0	1.82			3.03	1.55
2.5	3.09			5.15	2.63
2.8	3.93			6.56	3.35
3.0	4.35			7.25	3.70
3.5	5.72	1.1		9.53	4.87
4.0	7.28			12.13	6.20
4.5	9.78			16.13	8.33
4.8	10.43			16.58	8.89
5.0	11.79			18.74	10.04
5.5	14.62			23.23	12.45
6.0	17.40			27.66	14.82

操纵用钢丝绳 技术参数 Technical parameter

1×12

公称直径 Nominal Diameter	伸长率 Elongation		绳最小破断拉力 Min B/L	参考重量 Approximate Weight
	弹性 Elastic	永久 Permanent		
mm	不大于, % Not Exceed		kN	kg/100m
1.0	0.8	0.2	1.05	0.49
1.2			1.50	0.70
1.4			2.00	0.95
1.5			2.30	1.09
1.6			2.50	1.24
1.8			3.10	1.56
2.0			3.90	1.95
2.5			5.60	3.05
2.8			7.35	3.80
3.0			8.40	4.40