

6×19+IWS

公称直径 Nominal Diameter	公称抗拉强度 Nominal Tensile Strength, MPa				参考重量 Approximate weight kg/100m
	1960	2060	2160	2260	
mm	最小破断拉力 Minimum breaking force kN				
4.0	12.6	13.2	13.8	14.5	6.4
4.8	17.4	18.3	19.2	20.1	9.5
5.4	22.0	23.1	24.3	25.4	11.4
6.0	27.5	28.9	30.3	31.7	14.4
6.4	29.9	31.5	33.0	34.5	16.3
7.2	38.2	40.2	42.1	44.1	20.4
8.0	47.3	49.8	52.2	54.6	25.0
8.6	54.3	57.1	59.9	62.7	29.6
9.2	62.3	65.5	68.7	71.8	33.4
9.5	67.0	70.4	73.9	77.3	35.8

6×19W+IWS

公称直径 Nominal Diameter	公称抗拉强度 Nominal Tensile Strength, MPa				参考重量 Approximate weight kg/100m
	1960	2060	2160	2260	
mm	最小破断拉力 Minimum breaking force kN				
4.0	13.0	13.7	14.3	15.0	6.9
4.8	18.8	19.7	20.7	21.7	9.9
5.4	23.6	24.8	26.0	27.2	12.9
6.0	30.0	31.5	33.0	34.6	15.9
6.4	33.3	35.0	36.7	38.4	18.1
7.2	41.1	43.2	45.3	47.4	22.5
8.0	51.8	54.4	57.1	59.7	27.0
8.1	53.0	55.5	58.1	61.0	28.2
8.3	55.5	58.3	61.2	64.0	29.6
8.6	59.5	62.5	65.5	68.6	32.5
9.2	67.3	70.8	74.2	77.7	36.2
9.5	72.6	76.3	80.0	83.8	37.5
10.0	82.7	86.9	91.1	95.4	41.6
11.0	95.7	100.5	105.4	110.3	51.5
12.0	116.9	122.8	128.8	134.8	59.9

注：根据顾客需要，还可提供其他规格、抗拉强度的产品 NOTE:Providing engineer design sa per customer's request