

特高强度 Extra-High-Strength

直径 Diameter	抗拉强度 Tensile Strength	1%伸长应力 Stree at 1% Elongation	伸长率 Elongation Lo=250mm
mm	MPa	MPa	%
1.27~2.28	≥1825	≥1550	≥3.0
2.29~3.04	≥1790	≥1515	≥3.0
3.05~3.55	≥1760	≥1480	≥3.5
3.56~4.82	≥1725	≥1450	≥3.5

超高强度 Ultra-High-Strength

直径 Diameter	抗拉强度 Tensile Strength	1%伸长应力 Stree at 1% Elongation	伸长率 Elongation Lo=250mm
mm	MPa	MPa	%
1.27~2.28	≥1965	≥1580	≥3.0
2.29~3.04	≥1900	≥1550	≥3.0
3.05~3.55	≥1860	≥1515	≥3.5
3.56~4.82	≥1825	≥1480	≥3.5

锌层重量 Zinc coating

直径 Diameter	最小锌层重量 Minimum mass of coating
mm	g/m ²
1.27~1.52	183
1.53~1.90	198
1.91~2.28	214
2.29~2.64	229
2.65~3.04	244
3.05~3.55	259
3.56~4.57	274
4.58~4.82	305

按GB、EN、IEC、JIS、ASTM等，也可根据顾客的技术要求生产。
As per GB、EN、IEC、JIS、ASTM standard, as well as customer' s request.