

铠装电缆钢丝 典型参数 Typical parameters

公称直径 Nominal Diameter mm	低碳 Low carbon, tempered		高碳 high carbon, hard-drawn	
	直径公差 mm	抗拉强度 MPa	直径公差 mm	抗拉强度 MPa
0.8	±0.03	350-500	±0.01	1770-2060
0.9	±0.03		±0.01	1770-2060
1.0	±0.03		±0.01	1770-2060
1.2	±0.05		±0.02	1770-2060
1.4	±0.05		±0.02	1570-1960
1.6	±0.05		±0.02	1570-1960
1.8	±0.05			
2.0	±0.05			
2.2	±0.08			
2.3	±0.08			
2.6	±0.08			
2.9	±0.08			
3.2	±0.08			

按YB、EN、ISO、JIS、ASTM等，也可根据客户的技术要求生产。
As per YB、EN、ISO、JIS、ASTM standard, as well as customer' s request