

1×19

公称直径 Nominal Diameter		近似重量 Approximate weight	公称抗拉强度 Nominal Tensile Strength, MPa				
			1870	1960	2060	2160	2260
d	允许偏差 Tolerance		钢丝绳最小破断拉力 Min. breaking load				
mm	%	kg/100m	kN				
2.0	+5 0	1.97	4.2	4.4	4.7	4.9	5.1
2.5		3.08	6.6	6.9	7.3	7.7	8.0
3.0		4.49	9.5	10.0	10.5	11.0	11.5
3.5		6.02	13.0	13.6	14.3	15.0	15.7
4.0		7.90	17.0	17.8	18.7	19.6	20.5

1×19W

公称直径 Nominal Diameter		近似重量 Approximate weight	公称抗拉强度 Nominal Tensile Strength, MPa				
			1870	1960	2060	2160	2260
d	允许偏差 Tolerance		钢丝绳最小破断拉力 Min. breaking load				
mm	%	kg/100m	kN				
2.0	+5 0	2.16	4.6	4.8	5.0	5.3	5.5
2.5		3.70	7.6	8.0	8.4	8.8	9.2
3.0		4.69	10.1	10.6	11.1	11.7	12.2
3.5		6.70	14.6	15.3	16.1	16.9	17.7
4.0		8.40	18.3	19.2	20.2	21.2	22.1

1×25Fi/1×29Fi

公称直径 Nominal Diameter		近似重量 Approximate weight	公称抗拉强度 Nominal Tensile Strength, MPa				
			1870	1960	2060	2160	2260
d	允许偏差 Tolerance		钢丝绳最小破断拉力 Min. breaking load				
mm	%	kg/100m	kN				
4.0	+5 0	8.48	18.5	19.4	20.4	21.4	22.4
4.6		11.40	24.3	25.5	26.8	28.1	29.4
4.8		12.53	27.1	28.4	29.8	31.3	32.7
5.2		14.75	32.0	33.5	35.2	36.9	38.7
5.4		15.82	34.2	35.8	37.6	39.5	4.3
5.5		16.50	35.6	37.3	39.2	41.2	43.1
6.0		19.20	41.6	43.6	45.8	48.1	50.3
6.5		22.78	49.4	51.7	54.4	57.0	59.6
7.0		26.42	57.3	60	63.1	66.1	69.1

注：根据顾客需要，还可提供其他规格、抗拉强度的产品 NOTE:Providing engineer design sa per customer's request